

Bruck Norcote

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Basic properties	ISO								
Basis Weight	(ISO 536)	(g/m ²)	51	54	57	60	65	70	80
Thickness	(ISO 534)	(µm)	47	49	51	52	56	60	67
Bulk	(ISO 534)	(cm ³ /g)	0.92	0.91	0.89	0.87	0.86	0.86	0.84
Brightness D65	(ISO 2470)	(%)	75	75	75	76	76	76	76
CIE Whiteness	(ISO 11475)	(%)	71	71	71	71	72	73	74
L-value D65	(ISO 5631-2)	(D65/10°)	90	90	90	90	91	91	91
a-value D65	(ISO 5631-2)	(D65/10°)	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2
b-value D65	(ISO 5631-2)	(D65/10°)	1.5	1.5	1.3	1.3	1.3	1.3	1.3
Opacity.	(ISO 2471)	(%)	90	91	92	92	93	93	95
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	47	48	50	54	56	58	58
Smoothness PPS 10	(ISO 8791-4)	(µm)	1.3	1.3	1.3	1.2	1.2	1.2	1.2

Pre-press data	ISO								
CIE L*-value**	13655, M1	D50/2°	91	91	91	91	91	91	91
CIE a*-value**	13655, M1	D50/2°	0	0	0	0	0	0	0
CIE b*-value**	13655, M1	D50/2°	2.5	2.5	2.5	2.5	2.5	2.5	2.5

Recommended ICC-Profile: FOGRA 46L (PSO LWC Standard / ISO 12647-2:2013)

PRODUCT FAMILY:
Norcote

FINISH:
Gloss

Norske Skog Bruck is
certified according to:

PRINTING METHOD:
Heat set web offset

PRODUCER:
Bruck

Paper Profile
PEFC
FSC
EU Ecolabel
ISO 9001
ISO 14001
ISO 45001

*Last Updated:
February 2019*

We use cookies

Norske Skog ASA This website uses cookies to track your behavior and to improve your experience on the site. norskeskog.com
 You can always delete saved cookies by visiting the advanced settings of your browser. [Read more about our cookies.](#)

Do not accept cookies

Only accept functional cookies

Accept all cookies