

# Bruck Norcote Silk

**Utilización final:** Magazines, catalogues, supplements, direct mail, inserts/flyers

| Propiedad          | ISO                       |                      |      |      |      |      |      |      |      |      |
|--------------------|---------------------------|----------------------|------|------|------|------|------|------|------|------|
| Gramaje            | (ISO 536)                 | (g/m <sup>2</sup> )  | 54   | 57   | 60   | 65   | 70   | 75*  | 80   | 90   |
| Espesor            | (ISO 534)                 | (µm)                 | 60   | 57   | 58   | 62   | 67   | 71   | 75   | 85   |
| Volumen Específico | (ISO 534)                 | (cm <sup>3</sup> /g) | 1.10 | 1.00 | 1.00 | 0.95 | 0.95 | 0.95 | 0.94 | 0.94 |
| Blancura D 65      | (ISO 2470)                | (%)                  | 86   | 86   | 86   | 88   | 88   | 88   | 88   | 88   |
| Blancura CIE       | (ISO 11475)               | (%)                  | 100  | 102  | 102  | 105  | 107  | 107  | 107  | 107  |
| Tonalidad L D 65   | (ISO 5631-2)              | (D65/10°)            | 91   | 91   | 92   | 92   | 92   | 93   | 93   | 93   |
| Tonalidad A D 65   | (ISO 5631-2)              | (D65/10°)            | 0.2  | 0.2  | 0.2  | 0.8  | 0.8  | 0.8  | 0.8  | 0.8  |
| Tonalidad B D 65   | (ISO 5631-2)              | (D65/10°)            | -4.1 | -4.3 | -4.6 | -5.2 | -5.2 | -5.2 | -5.2 | -5.2 |
| Opacidad           | (ISO 2471)                | (%)                  | 91   | 92   | 92   | 93   | 94   | 95   | 95   | 96   |
| Brillo (Lehman)    | (ISO 8254-1) (Tappi T480) | (%)                  | 16   | 23   | 26   | 29   | 32   | 35   | 36   | 37   |
| Lisura PPS 10      | (ISO 8791-4)              | (µm)                 | 2.5  | 2.5  | 2.5  | 2.5  | 2.5  | 2.5  | 2.5  | 2.5  |

| Pre-press datos | ISO       |        |      |      |      |      |      |      |      |      |
|-----------------|-----------|--------|------|------|------|------|------|------|------|------|
| CIE L*-value**  | 13655, M1 | D50/2° | 91.5 | 91.5 | 92   | 92   | 92   | 92.5 | 92.5 | 92.5 |
| CIE a*-value**  | 13655, M1 | D50/2° | -0.3 | -0.3 | -0.3 | -0.5 | -0.5 | -0.5 | -0.5 | -0.5 |
| CIE b*-value**  | 13655, M1 | D50/2° | -1.0 | -1.0 | -1.2 | -1.5 | -1.5 | -1.5 | -1.5 | -1.5 |

**Recomendada ICC-Perfil:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:  
Norcote

SISTEMA DE IMPRESIÓN:  
Heat set web offset

*Last Updated:  
January 2019*

ACABADO:  
Silk

PRODUCTOR:  
Bruck

Norske Skog Bruck  
tiene la certificación:

Paper Profile  
PEFC  
FSC  
EU Ecolabel  
ISO 9001  
ISO 14001  
ISO 45001