

Bruck Norcote Silk H

Utilización final: Magazines, catalogues, supplements, direct mail, inserts/flyers

Propiedad	ISO									
Gramaje	(ISO 536)	(g/m ²)	54	57	60	65	70	75*	80	90
Espesor	(ISO 534)	(µm)	60	57	58	62	67	71	75	85
Volumen Específico	(ISO 534)	(cm ³ /g)	1.10	1.00	1.00	0.95	0.95	0.95	0.94	0.94
Blancura D 65	(ISO 2470)	(%)	86	86	86	88	88	88	88	88
Blancura CIE	(ISO 11475)	(%)	100	102	102	105	107	107	107	107
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	91	91	92	92	92	93	93	93
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	0.2	0.2	0.2	0.8	0.8	0.8	0.8	0.8
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	-4.1	-4.3	-4.6	-5.2	-5.2	-5.2	-5.2	-5.2
Opacidad	(ISO 2471)	(%)	91	92	92	93	94	95	95	96
Brillo (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	16	23	26	29	32	35	36	37
Lisura PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5

Pre-press datos	ISO									
CIE L*-value**	13655, M1	D50/2°	91.5	91.5	92	92	92	92.5	92.5	92.5
CIE a*-value**	13655, M1	D50/2°	-0.3	-0.3	-0.3	-0.5	-0.5	-0.5	-0.5	-0.5
CIE b*-value**	13655, M1	D50/2°	-1.0	-1.0	-1.2	-1.5	-1.5	-1.5	-1.5	-1.5

Recomendada ICC-Perfil: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:
Norcote

SISTEMA DE IMPRESIÓN:
Heat set web offset

*Last Updated:
January 2019*

ACABADO:
Silk

PRODUCTOR:
Bruck

Norske Skog Bruck
tiene la certificación:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)