

Bruck Norcote Satin

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Basic properties	ISO								
Basis Weight	(ISO 536)	(g/m ²)	54*	57*	60*	65*	70*	80*	
Thickness	(ISO 534)	(µm)	54	57	59	64	67	75	
Bulk	(ISO 534)	(cm ³ /g)	1.00	1.00	0.98	0.98	0.96	0.94	
Brightness D65	(ISO 2470)	(%)	76	76	76	76	76	76	
CIE Whiteness	(ISO 11475)	(%)	73	73	73	73	73	73	
L-value D65	(ISO 5631-2)	(D65/10°)	90	91	91	91	91	91	
a-value D65	(ISO 5631-2)	(D65/10°)	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2	
b-value D65	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2	1.2	
Opacity.	(ISO 2471)	(%)	91	92	93	94	94	95	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	20	25	28	33	35	36	
Smoothness PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	

Pre-press data	ISO								
CIE L*-value**	13655, M1	D50/2°	91	91	91	91	91	91	
CIE a*-value**	13655, M1	D50/2°	0	0	0	0	0	0	
CIE b*-value**	13655, M1	D50/2°	2.5	2.5	2.5	2.5	2.5	2.5	

Recommended ICC-Profile: FOGRA 46L (PSO LWC Standard / ISO 12647-2:2013)

PRODUCT FAMILY:
Norcote

FINISH:
Silk

PRINTING METHOD:
Heat set web offset

PRODUCER:
Bruck

*Last Updated:
January 2019*

Norske Skog Bruck is
certified according to:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)