

Bruck Norcote Satin H

Anwendung: Magazines, catalogues, supplements, direct mail, inserts/flyers

Grundlegende Merkmale	ISO								
Flächenbezogene Masse	(ISO 536)	(g/m ²)	54*	57*	60*	65*	70*	80*	
Dicke	(ISO 534)	(µm)	54	57	59	64	67	75	
Spez. Volumen	(ISO 534)	(cm ³ /g)	1.00	1.00	0.98	0.98	0.96	0.94	
Weisse, D65/10 (UV)	(ISO 2470)	(%)	76	76	76	76	76	76	
Weisse CIE	(ISO 11475)	(%)	73	73	73	73	73	73	
L*	(ISO 5631-2)	(D65/10°)	90	91	91	91	91	91	
a*	(ISO 5631-2)	(D65/10°)	-0.2	-0.2	-0.2	-0.2	-0.2	-0.2	
b*	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2	1.2	
Opazität	(ISO 2471)	(%)	91	92	93	94	94	95	
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	20	25	28	33	35	36	
Glätte	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	

Pre-press Daten	ISO								
CIE L*-value**	13655, M1	D50/2°	91	91	91	91	91	91	
CIE a*-value**	13655, M1	D50/2°	0	0	0	0	0	0	
CIE b*-value**	13655, M1	D50/2°	2.5	2.5	2.5	2.5	2.5	2.5	

Empfohlenes ICC-Profil: FOGRA 46L (PSO LWC Standard / ISO 12647-2:2013)

PRODUKTFAMILIE:
Norcote

OBERFLÄCHE:
Silk

DRUCKVERFAHREN:
Heat set web offset

HERSTELLER:
Bruck

*Last Updated:
January 2019*

Norske Skog Bruck ist
zertifiziert nach:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)