

# Bruck Norcote Top

**End use:** Magazines, catalogues, supplements, direct mail, inserts/flyers

Basic properties	ISO								
Basis Weight	(ISO 536)	(g/m <sup>2</sup> )	65	70	75*	80	90	100	
Thickness	(ISO 534)	(µm)	56	59	63	68	75	81	
Bulk	(ISO 534)	(cm <sup>3</sup> /g)	0.86	0.84	0.84	0.85	0.83	0.81	
Brightness D65	(ISO 2470)	(%)	92	92	92	93	93	94	
CIE Whiteness	(ISO 11475)	(%)	118	118	118	118	118	118	
L-value D65	(ISO 5631-2)	(D65/10°)	92	93	93	93	93	93	
a-value D65	(ISO 5631-2)	(D65/10°)	0.8	0.8	1.0	1.0	1.0	1.0	
b-value D65	(ISO 5631-2)	(D65/10°)	-7.2	-7.2	-7.2	-7.8	-7.8	-7.8	
Opacity.	(ISO 2471)	(%)	92	93	94	95	96	96	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	56	58	59	60	60	60	
Smoothness PPS 10	(ISO 8791-4)	(µm)	1.2	1.2	1.2	1.2	1.2	1.2	

Pre-press data	ISO								
CIE L*-value**	13655, M1	D50/2°	92.5	92.5	92.5	92.5	92.5	92.5	92.5
CIE a*-value**	13655, M1	D50/2°	0.4	0.4	0.5	0.5	0.5	0.5	0.5
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.3	-3.3	-3.3	-3.3

**Recommended ICC-Profile:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

PRODUCT FAMILY:  
Norcote

FINISH:  
Gloss

PRINTING METHOD:  
Heat set web offset

PRODUCER:  
Bruck

*Last Updated:  
January 2019*

Norske Skog Bruck is  
certified according to:

Paper Profile  
PEFC (ENG)  
FSC  
EU Ecolabel  
ISO 14001: 2009  
ISO 9001: 2008  
ISO 18001: 2007  
PEFC (DE)