

# Bruck Norcote Top H

**Utilización final:** Magazines, catalogues, supplements, direct mail, inserts/flyers

| Propiedad          | ISO                       |                      |      |      |      |      |      |      |  |
|--------------------|---------------------------|----------------------|------|------|------|------|------|------|--|
| Gramaje            | (ISO 536)                 | (g/m <sup>2</sup> )  | 65   | 70   | 75*  | 80   | 90   | 100  |  |
| Espesor            | (ISO 534)                 | (µm)                 | 56   | 59   | 63   | 68   | 75   | 81   |  |
| Volumen Específico | (ISO 534)                 | (cm <sup>3</sup> /g) | 0.86 | 0.84 | 0.84 | 0.85 | 0.83 | 0.81 |  |
| Blancura D 65      | (ISO 2470)                | (%)                  | 92   | 92   | 92   | 93   | 93   | 94   |  |
| Blancura CIE       | (ISO 11475)               | (%)                  | 118  | 118  | 118  | 118  | 118  | 118  |  |
| Tonalidad L D 65   | (ISO 5631-2)              | (D65/10°)            | 92   | 93   | 93   | 93   | 93   | 93   |  |
| Tonalidad A D 65   | (ISO 5631-2)              | (D65/10°)            | 0.8  | 0.8  | 1.0  | 1.0  | 1.0  | 1.0  |  |
| Tonalidad B D 65   | (ISO 5631-2)              | (D65/10°)            | -7.2 | -7.2 | -7.2 | -7.8 | -7.8 | -7.8 |  |
| Opacidad           | (ISO 2471)                | (%)                  | 92   | 93   | 94   | 95   | 96   | 96   |  |
| Brillo (Lehman)    | (ISO 8254-1) (Tappi T480) | (%)                  | 56   | 58   | 59   | 60   | 60   | 60   |  |
| Lisura PPS 10      | (ISO 8791-4)              | (µm)                 | 1.2  | 1.2  | 1.2  | 1.2  | 1.2  | 1.2  |  |

| Pre-press datos | ISO       |        |      |      |      |      |      |      |      |
|-----------------|-----------|--------|------|------|------|------|------|------|------|
| CIE L*-value**  | 13655, M1 | D50/2° | 92.5 | 92.5 | 92.5 | 92.5 | 92.5 | 92.5 | 92.5 |
| CIE a*-value**  | 13655, M1 | D50/2° | 0.4  | 0.4  | 0.5  | 0.5  | 0.5  | 0.5  | 0.5  |
| CIE b*-value**  | 13655, M1 | D50/2° | -3.0 | -3.0 | -3.0 | -3.3 | -3.3 | -3.3 | -3.3 |

**Recomendada ICC-Perfil:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:  
Norcote

SISTEMA DE IMPRESIÓN:  
Heat set web offset

*Last Updated:  
January 2019*

ACABADO:  
Gloss

PRODUCTOR:  
Bruck

Norske Skog Bruck  
tiene la certificación:

Paper Profile  
PEFC (ENG)  
FSC  
EU Ecolabel  
ISO 14001: 2009  
ISO 9001: 2008  
ISO 18001: 2007  
PEFC (DE)