

Bruck Norcote Top

Utilización final: Magazines, catalogues, supplements, direct mail, inserts/flyers

Propiedad	ISO								
Gramaje	(ISO 536)	(g/m ²)	65	70	75*	80	90	100	
Espesor	(ISO 534)	(µm)	56	59	63	68	75	81	
Volumen Específico	(ISO 534)	(cm ³ /g)	0.86	0.84	0.84	0.85	0.83	0.81	
Blancura D 65	(ISO 2470)	(%)	92	92	92	93	93	94	
Blancura CIE	(ISO 11475)	(%)	118	118	118	118	118	118	
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	92	93	93	93	93	93	
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	0.8	0.8	1.0	1.0	1.0	1.0	
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	-7.2	-7.2	-7.2	-7.8	-7.8	-7.8	
Opacidad	(ISO 2471)	(%)	92	93	94	95	96	96	
Brillo (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	56	58	59	60	60	60	
Lisura PPS 10	(ISO 8791-4)	(µm)	1.2	1.2	1.2	1.2	1.2	1.2	

Pre-press datos	ISO								
CIE L*-value**	13655, M1	D50/2°	92.5	92.5	92.5	92.5	92.5	92.5	92.5
CIE a*-value**	13655, M1	D50/2°	0.4	0.4	0.5	0.5	0.5	0.5	0.5
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.3	-3.3	-3.3	-3.3

Recomendada ICC-Perfil: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:
Norcote

SISTEMA DE IMPRESIÓN:
Heat set web offset

*Last Updated:
January 2019*

ACABADO:
Gloss

PRODUCTOR:
Bruck

Norske Skog Bruck
tiene la certificación:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 14001: 2009
ISO 9001: 2008
ISO 18001: 2007
PEFC (DE)