

Bruck Norcote Top

Anwendung: Magazines, catalogues, supplements, direct mail, inserts/flyers

Grundlegende Merkmale	ISO								
Flächenbezogene Masse	(ISO 536)	(g/m ²)	65	70	75*	80	90	100	
Dicke	(ISO 534)	(µm)	56	59	63	68	75	81	
Spez. Volumen	(ISO 534)	(cm ³ /g)	0.86	0.84	0.84	0.85	0.83	0.81	
Weisse, D65/10 (UV)	(ISO 2470)	(%)	92	92	92	93	93	94	
Weisse CIE	(ISO 11475)	(%)	118	118	118	118	118	118	
L*	(ISO 5631-2)	(D65/10°)	92	93	93	93	93	93	
a*	(ISO 5631-2)	(D65/10°)	0.8	0.8	1.0	1.0	1.0	1.0	
b*	(ISO 5631-2)	(D65/10°)	-7.2	-7.2	-7.2	-7.8	-7.8	-7.8	
Opazität	(ISO 2471)	(%)	92	93	94	95	96	96	
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	56	58	59	60	60	60	
Glätte	(ISO 8791-4)	(µm)	1.2	1.2	1.2	1.2	1.2	1.2	

Pre-press Daten	ISO								
CIE L*-value**	13655, M1	D50/2°	92.5	92.5	92.5	92.5	92.5	92.5	92.5
CIE a*-value**	13655, M1	D50/2°	0.4	0.4	0.5	0.5	0.5	0.5	0.5
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.3	-3.3	-3.3	-3.3

Empfohlenes ICC-Profil: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

PRODUKTFAMILIE:
Norcote

OBERFLÄCHE:
Gloss

DRUCKVERFAHREN:
Heat set web offset

HERSTELLER:
Bruck

*Last Updated:
January 2019*

Norske Skog Bruck ist
zertifiziert nach:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 14001: 2009
ISO 9001: 2008
ISO 18001: 2007
PEFC (DE)