

Bruck Norcote Trend H

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

Basic properties	ISO							
Basis Weight	(ISO 536)	(g/m ²)	65	70	75*	80	90	
Thickness	(ISO 534)	(µm)	62	67	71	75	83	
Bulk	(ISO 534)	(cm ³ /g)	0.95	0.96	0.95	0.94	0.92	
Brightness D65	(ISO 2470)	(%)	92	93	94	94	95	
CIE Whiteness	(ISO 11475)	(%)	120	120	120	120	120	
L-value D65	(ISO 5631-2)	(D65/10°)	93	93	94	94	94	
a-value D65	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2	
b-value D65	(ISO 5631-2)	(D65/10°)	-7.4	-7.5	-7.5	-7.5	-7.5	
Opacity.	(ISO 2471)	(%)	94	95	95	95	96	
Gloss (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	32	32	35	36	37	
Smoothness PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	

Pre-press data	ISO							
CIE L*-value**	13655, M1	D50/2°	93	93	93	93	93	
CIE a*-value**	13655, M1	D50/2°	0.5	0.5	0.5	0.5	0.5	
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.0	-3.0	

Recommended ICC-Profile: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

PRODUCT FAMILY:
Norcote

FINISH:
Silk

PRINTING METHOD:
Heat set web offset

PRODUCER:
Bruck

*Last Updated:
January 2019*

Norske Skog Bruck is
certified according to:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)