

# Bruck Norcote Trend

**Utilización final:** Magazines, catalogues, supplements, direct mail, inserts/flyers

Propiedad	ISO								
Gramaje	(ISO 536)	(g/m <sup>2</sup> )	65	70	75*	80	90	100	
Espesor	(ISO 534)	(µm)	62	67	71	75	83	94	
Volumen Específico	(ISO 534)	(cm <sup>3</sup> /g)	0.95	0.96	0.95	0.94	0.92	0.94	
Blancura D 65	(ISO 2470)	(%)	92	93	94	94	95	95	
Blancura CIE	(ISO 11475)	(%)	120	120	120	120	120	120	
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	93	93	94	94	94	94	
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2	1.2	
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	-7.4	-7.5	-7.5	-7.5	-7.5	-7.5	
Opacidad	(ISO 2471)	(%)	94	95	95	95	96	96	
Brillo (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	32	32	35	36	37	37	
Lisura PPS 10	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	

Pre-press datos	ISO								
CIE L*-value**	13655, M1	D50/2°	93	93	93	93	93	93	93
CIE a*-value**	13655, M1	D50/2°	0.5	0.5	0.5	0.5	0.5	0.5	0.5
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.0	-3.0	-3.0	-3.0

**Recomendada ICC-Perfil:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:  
Norcote

SISTEMA DE IMPRESIÓN:  
Heat set web offset

*Last Updated:  
October 2020*

ACABADO:  
Silk

PRODUCTOR:  
Bruck

Norske Skog Bruck  
tiene la certificación:

Paper Profile  
PEFC  
FSC  
EU Ecolabel  
ISO 9001  
ISO 14001  
ISO 45001