

Bruck Norcote Trend H

Utilización final: Magazines, catalogues, supplements, direct mail, inserts/flyers

| Propiedad | ISO | | | | | | | |
|--------------------|---------------------------|----------------------|------|------|------|------|------|--|
| Gramaje | (ISO 536) | (g/m ²) | 65 | 70 | 75* | 80 | 90 | |
| Espesor | (ISO 534) | (µm) | 62 | 67 | 71 | 75 | 83 | |
| Volumen Específico | (ISO 534) | (cm ³ /g) | 0.95 | 0.96 | 0.95 | 0.94 | 0.92 | |
| Blancura D 65 | (ISO 2470) | (%) | 92 | 93 | 94 | 94 | 95 | |
| Blancura CIE | (ISO 11475) | (%) | 120 | 120 | 120 | 120 | 120 | |
| Tonalidad L D 65 | (ISO 5631-2) | (D65/10°) | 93 | 93 | 94 | 94 | 94 | |
| Tonalidad A D 65 | (ISO 5631-2) | (D65/10°) | 1.2 | 1.2 | 1.2 | 1.2 | 1.2 | |
| Tonalidad B D 65 | (ISO 5631-2) | (D65/10°) | -7.4 | -7.5 | -7.5 | -7.5 | -7.5 | |
| Opacidad | (ISO 2471) | (%) | 94 | 95 | 95 | 95 | 96 | |
| Brillo (Lehman) | (ISO 8254-1) (Tappi T480) | (%) | 32 | 32 | 35 | 36 | 37 | |
| Lisura PPS 10 | (ISO 8791-4) | (µm) | 2.5 | 2.5 | 2.5 | 2.5 | 2.5 | |

| Pre-press datos | ISO | | | | | | | |
|-----------------|-----------|--------|------|------|------|------|------|--|
| CIE L*-value** | 13655, M1 | D50/2° | 93 | 93 | 93 | 93 | 93 | |
| CIE a*-value** | 13655, M1 | D50/2° | 0.5 | 0.5 | 0.5 | 0.5 | 0.5 | |
| CIE b*-value** | 13655, M1 | D50/2° | -3.0 | -3.0 | -3.0 | -3.0 | -3.0 | |

Recomendada ICC-Perfil: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:
Norcote

SISTEMA DE IMPRESIÓN:
Heat set web offset

*Last Updated:
January 2019*

ACABADO:
Silk

PRODUCTOR:
Bruck

Norske Skog Bruck
tiene la certificación:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)