

# Bruck Norcote Trend

**Anwendung:** Magazines, catalogues, supplements, direct mail, inserts/flyers

Grundlegende Merkmale	ISO								
Flächenbezogene Masse	(ISO 536)	(g/m <sup>2</sup> )	65	70	75*	80	90	100	
Dicke	(ISO 534)	(µm)	62	67	71	75	83	94	
Spez. Volumen	(ISO 534)	(cm <sup>3</sup> /g)	0.95	0.96	0.95	0.94	0.92	0.94	
Weisse, D65/10 (UV)	(ISO 2470)	(%)	92	93	94	94	95	95	
Weisse CIE	(ISO 11475)	(%)	120	120	120	120	120	120	
L*	(ISO 5631-2)	(D65/10°)	93	93	94	94	94	94	
a*	(ISO 5631-2)	(D65/10°)	1.2	1.2	1.2	1.2	1.2	1.2	
b*	(ISO 5631-2)	(D65/10°)	-7.4	-7.5	-7.5	-7.5	-7.5	-7.5	
Opazität	(ISO 2471)	(%)	94	95	95	95	96	96	
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	32	32	35	36	37	37	
Glätte	(ISO 8791-4)	(µm)	2.5	2.5	2.5	2.5	2.5	2.5	

Pre-press Daten	ISO								
CIE L*-value**	13655, M1	D50/2°	93	93	93	93	93	93	93
CIE a*-value**	13655, M1	D50/2°	0.5	0.5	0.5	0.5	0.5	0.5	0.5
CIE b*-value**	13655, M1	D50/2°	-3.0	-3.0	-3.0	-3.0	-3.0	-3.0	-3.0

**Empfohlenes ICC-Profil:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

PRODUKTFAMILIE:  
Norcote

OBERFLÄCHE:  
Silk

DRUCKVERFAHREN:  
Heat set web offset

HERSTELLER:  
Bruck

*Last Updated:  
October 2020*

Norske Skog Bruck ist  
zertifiziert nach:

Paper Profile  
PEFC  
FSC  
EU Ecolabel  
ISO 9001  
ISO 14001  
ISO 45001