

Saugbrugs NorSC Value

Utilización final: Magazines, inserts, catalogues, direct mail and door drop.

Propiedad	ISO					
Gramaje	(ISO 536)	(g/m ²)	42*	45	47.4	52
Espesor	(ISO 534)	(µm)	42	45	47.4	52
Densidad	(ISO 534)	(kg/m ³)	1000	1000	1000	1000
Volumen Específico	(ISO 534)	(cm ³ /g)	1.00	1.00	1.00	1.00
Blancura D 65	(ISO 2470)	(%)	65	65	65	65
Blancura CIE	(ISO 11475)	(%)	45	45	45	45
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	86.5	86.5	86.5	86.5
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	-1.5	-1.5	-1.5	-1.5
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	5.5	5.5	5.5	5.5
Opacidad	(ISO 2471)	(%)	89	91	92	94
Brillo (Hunter)	(ISO 8254-1)	(%)	35	35	35	35
Lisura PPS 10	(ISO 8791-4)	(µm)	1.8	1.7	1.7	1.6

FAMILIA DE PRODUCTOS:

ACABADO:
SC

SISTEMA DE IMPRESIÓN:
Heatset & Rotogravure
Characterization data:
Fogra 40

PRODUCTOR:
Saugbrugs

*Last Updated:
May 2019*

Norske Skog
Saugbrugs tiene la
certificación:

EU Ecolabel
PEFC
FSC
EU Timber Regulation
ISO 50001:2011
ISO 9001:2015
ISO 14001:2015
Paper Profile
EU Timber Regulation