

Saugbrugs NorSC Polar

Utilización final: Magazines, inserts, catalogues, direct mail and door drop.

Product Family: SC

Propiedad	ISO									
Gramaje	(ISO 536)	(g/m ²)	42	45	47.4	51	54	57	60	65
Espesor	(ISO 534)	(µm)	42	44	46	47	49	51	54	57
Densidad	(ISO 534)	(kg/m ³)	1000	1020	1040	1080	1100	1120	1120	1140
Volumen Específico	(ISO 534)	(cm ³ /g)	1.00	0.98	0.96	0.93	0.91	0.89	0.89	0.87
Blancura D 65	(ISO 2470)	(%)	75	76	78	80	80	80	80	80
Blancura CIE	(ISO 11475)	(%)	74	75	77	78	78	78	78	78
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	89	89	89	89	89	89	89	89
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	0.1	0.1	0.1	0.1	0.1	0.1	0.1	0.1
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8	-0.8
Opacidad	(ISO 2471)	(%)	89	90	91	92	93	94	95	96
Brillo (Hunter)	(ISO 8254-1)	(%)	38	40	43	46	46	46	46	46
Lisura PPS 10	(ISO 8791-4)	(µm)	1.20	1.20	1.20	1.20	1.20	1.20	1.20	1.20

FAMILIA DE PRODUCTOS:
Nor

SISTEMA DE IMPRESIÓN:
Heatset & Rotogravure

CHARACTERIZATION DATA:
Fogra 46

*Last Updated:
October 2020*

ACABADO:
Gloss

PRODUCTOR:
Saugbrugs

Norske Skog
Saugbrugs tiene la
certificación:

Paper Profile
PEFC
FSC
EU Timber Regulation
ISO 50001: 2011
ISO 9001: 2015
ISO 14001: 2015
EU Ecolabel
Norske Skog Saugbrugs -
Carbon Footprint