

Saugbrugs NorSC Polar

Anwendung: Magazines, inserts, catalogues, direct mail and door drop.

Product Family: SC

| Grundlegende Merkmale | ISO | | | | | | | | | |
|-----------------------|--------------|----------------------|------|------|------|------|------|------|------|------|
| Flächenbezogene Masse | (ISO 536) | (g/m ²) | 42 | 45 | 47.4 | 51 | 54 | 57 | 60 | 65 |
| Dicke | (ISO 534) | (µm) | 42 | 44 | 46 | 47 | 49 | 51 | 54 | 57 |
| Blattdichte | (ISO 534) | (kg/m ³) | 1000 | 1020 | 1040 | 1080 | 1100 | 1120 | 1120 | 1140 |
| Spez. Volumen | (ISO 534) | (cm ³ /g) | 1.00 | 0.98 | 0.96 | 0.93 | 0.91 | 0.89 | 0.89 | 0.87 |
| Weisse, D65/10 (UV) | (ISO 2470) | (%) | 75 | 76 | 78 | 80 | 80 | 80 | 80 | 80 |
| Weisse CIE | (ISO 11475) | (%) | 74 | 75 | 77 | 78 | 78 | 78 | 78 | 78 |
| L* | (ISO 5631-2) | (D65/10°) | 89 | 89 | 89 | 89 | 89 | 89 | 89 | 89 |
| a* | (ISO 5631-2) | (D65/10°) | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 | 0.1 |
| b* | (ISO 5631-2) | (D65/10°) | -0.8 | -0.8 | -0.8 | -0.8 | -0.8 | -0.8 | -0.8 | -0.8 |
| Opazität | (ISO 2471) | (%) | 89 | 90 | 91 | 92 | 93 | 94 | 95 | 96 |
| Glanz (Hunter) | (ISO 8254-1) | (%) | 38 | 40 | 43 | 46 | 46 | 46 | 46 | 46 |
| Glätte | (ISO 8791-4) | (µm) | 1.20 | 1.20 | 1.20 | 1.20 | 1.20 | 1.20 | 1.20 | 1.20 |

PRODUKTFAMILIE:
Nor

OBERFLÄCHE:
Gloss

DRUCKVERFAHREN:
Heatset & Rotogravure

HERSTELLER:
Saugbrugs

CHARACTERIZATION
DATA:
Fogra 46

*Last Updated:
October 2020*

Norske Skog
Saugbrugs ist
zertifiziert nach:

Paper Profile
PEFC
FSC
EU Timber Regulation
ISO 50001: 2011
ISO 9001: 2015
ISO 14001: 2015
EU Ecolabel
Norske Skog Saugbrugs -
Carbon Footprint