

# Bruck Norcote Super H

**Utilización final:** Magazines, catalogues, supplements, direct mail, inserts/flyers

Propiedad	ISO									
Gramaje	(ISO 536)	(g/m <sup>2</sup> )	54*	57	60	65	70	75	80	90
Espesor	(ISO 534)	(µm)	49	51	52	56	60	64	67	75
Volumen Específico	(ISO 534)	(cm <sup>3</sup> /g)	0.90	0.89	0.87	0.86	0.86	0.85	0.84	0.83
Blancura D 65	(ISO 2470)	(%)	85	85	85	87	87	87	87	87
Blancura CIE	(ISO 11475)	(%)	100	100	100	105	105	105	105	105
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	91	91	92	92	92	92	92	92
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	0.1	0.1	0.1	0.6	0.6	0.6	0.6	0.6
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	-4.1	-4.0	-4.1	-4.9	-4.9	-4.9	-4.9	-4.9
Opacidad	(ISO 2471)	(%)	90	91	92	92	93	94	95	96
Brillo (Lehman)	(ISO 8254-1) (Tappi T480)	(%)	48	50	54	56	58	58	58	58
Lisura PPS 10	(ISO 8791-4)	(µm)	1.3	1.3	1.2	1.2	1.2	1.2	1.2	1.2

Pre-press datos	ISO									
CIE L*-value**	13655, M1	D50/2°	91	91	92	92	92	92	92	92
CIE a*-value**	13655, M1	D50/2°	0.0	0.0	0.0	-0.3	-0.3	-0.3	-0.3	-0.3
CIE b*-value**	13655, M1	D50/2°	-0.7	-0.7	-0.7	-1.0	-1.0	-1.0	-1.0	-1.0

**Recomendada ICC-Perfil:** FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

FAMILIA DE PRODUCTOS:  
Norcote

SISTEMA DE IMPRESIÓN:  
Heat set web offset

*Last Updated:  
January 2019*

ACABADO:  
Gloss

PRODUCTOR:  
Bruck

Norske Skog Bruck  
tiene la certificación:

Paper Profile  
PEFC (ENG)  
FSC  
EU Ecolabel  
ISO 9001:2008  
ISO 14001:2004  
ISO 18001: 2007  
PEFC (DE)