

Bruck Norcote Super H

Anwendung: Magazines, catalogues, supplements, direct mail, inserts/flyers

Grundlegende Merkmale	ISO										
Flächenbezogene Masse	(ISO 536)	(g/m ²)	54*	57	60	65	70	75	80	90	
Dicke	(ISO 534)	(µm)	49	51	52	56	60	64	67	75	
Spez. Volumen	(ISO 534)	(cm ³ /g)	0.90	0.89	0.87	0.86	0.86	0.85	0.84	0.83	
Weisse, D65/10 (UV)	(ISO 2470)	(%)	85	85	85	87	87	87	87	87	
Weisse CIE	(ISO 11475)	(%)	100	100	100	105	105	105	105	105	
L*	(ISO 5631-2)	(D65/10°)	91	91	92	92	92	92	92	92	
a*	(ISO 5631-2)	(D65/10°)	0.1	0.1	0.1	0.6	0.6	0.6	0.6	0.6	
b*	(ISO 5631-2)	(D65/10°)	-4.1	-4.0	-4.1	-4.9	-4.9	-4.9	-4.9	-4.9	
Opazität	(ISO 2471)	(%)	90	91	92	92	93	94	95	96	
Glanz (Lehmann)	(ISO 8254-1) (Tappi T480)	(%)	48	50	54	56	58	58	58	58	
Glätte	(ISO 8791-4)	(µm)	1.3	1.3	1.2	1.2	1.2	1.2	1.2	1.2	

Pre-press Daten	ISO										
CIE L*-value**	13655, M1	D50/2°	91	91	92	92	92	92	92	92	92
CIE a*-value**	13655, M1	D50/2°	0.0	0.0	0.0	-0.3	-0.3	-0.3	-0.3	-0.3	-0.3
CIE b*-value**	13655, M1	D50/2°	-0.7	-0.7	-0.7	-1.0	-1.0	-1.0	-1.0	-1.0	-1.0

Empfohlenes ICC-Profil: FOGRA 45L (PSO LWC Improved / ISO 12647-2:2013)

PRODUKTFAMILIE:
Norcote

OBERFLÄCHE:
Gloss

DRUCKVERFAHREN:
Heat set web offset

HERSTELLER:
Bruck

*Last Updated:
January 2019*

Norske Skog Bruck ist
zertifiziert nach:

Paper Profile
PEFC (ENG)
FSC
EU Ecolabel
ISO 9001:2008
ISO 14001:2004
ISO 18001: 2007
PEFC (DE)