

# Saugbrugs Nor Opaq

**Utilización final:** Magazines, inserts, catalogues, direct mail and door drop.

**Product Family:** UMI

Propiedad	ISO							
Gramaje	(ISO 536)	(g/m <sup>2</sup> )	42	45	47.4	52	57	
Espesor	(ISO 534)	(µm)	53	55	55	57	60	
Densidad	(ISO 534)	(kg/m <sup>3</sup> )	800	820	860	910	950	
Volumen Específico	(ISO 534)	(cm <sup>3</sup> /g)	1.25	1.22	1.16	1.10	1.05	
Blancura D 65	(ISO 2470)	(%)	68	68	68	68	68	
Blancura CIE	(ISO 11475)	(%)	50	50	50	50	50	
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	87	87	87	87	87	
Tonalidad A D 65	(ISO 5631-2 )	(D65/10°)	-1.4	-1.4	-1.4	-1.4	-1.4	
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	4.5	4.5	4.5	4.5	4.5	
Opacidad	(ISO 2471)	(%)	93	94	95	97	97	
Brillo (Hunter)	(ISO 8254-1)	(%)	20-25	20-25	20-25	20-25	20-25	
Lisura PPS 10	(ISO 8791-4)	(µm)	1.7	1.7	1.7	1.7	1.7	

FAMILIA DE PRODUCTOS:  
Nor

SISTEMA DE IMPRESIÓN:  
Heatset & Rotogravure

CHARACTERIZATION DATA:

Heatset: Fogra 40L  
Gravure: ICC Paper profile -  
PSR\_MF\_V2\_M1.icc

ACABADO:  
Silk

PRODUCTOR:  
Saugbrugs

Norske Skog  
Saugbrugs tiene la  
certificación:

Paper Profile  
PEFC  
FSC  
EU Timber Regulation  
ISO 50001: 2018  
ISO 9001: 2015  
ISO 14001: 2015  
EU Ecolabel  
Norske Skog Saugbrugs -  
Carbon Footprint