

Saugbrugs Nor Opaq

Utilización final: Magazines, inserts, catalogues, direct mail and door drop.

Product Family: UMI

Propiedad	ISO							
Gramaje	(ISO 536)	(g/m ²)	42	45	47.4	52	57	
Espesor	(ISO 534)	(µm)	53	55	55	57	60	
Densidad	(ISO 534)	(kg/m ³)	800	820	860	910	950	
Volumen Específico	(ISO 534)	(cm ³ /g)	1.25	1.22	1.16	1.10	1.05	
Blancura D 65	(ISO 2470)	(%)	68	68	68	68	68	
Blancura CIE	(ISO 11475)	(%)	50	50	50	50	50	
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	87	87	87	87	87	
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	-1.4	-1.4	-1.4	-1.4	-1.4	
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	4.5	4.5	4.5	4.5	4.5	
Opacidad	(ISO 2471)	(%)	93	94	95	97	97	
Brillo (Hunter)	(ISO 8254-1)	(%)	20-25	20-25	20-25	20-25	20-25	
Lisura PPS 10	(ISO 8791-4)	(µm)	1.7	1.7	1.7	1.7	1.7	

FAMILIA DE PRODUCTOS:
Nor

SISTEMA DE IMPRESIÓN:
Heatset & Rotogravure

CHARACTERIZATION DATA:

Heatset: Fogra 40L
Gravure: ICC Paper profile - PSR_MF_V2_M1.icc

ACABADO:
Silk

PRODUCTOR:
Saugbrugs

Norske Skog Saugbrugs tiene la certificación:

Paper Profile
PEFC
FSC
EU Timber Regulation
ISO 50001: 2018
ISO 9001: 2015
ISO 14001: 2015
EU Ecolabel
Norske Skog Saugbrugs - Carbon Footprint