

Tasman Directory

End use: Telephone directories, catalogues

Basic properties	ISO		
Basis Weight	(ISO 536)	(g/m ²)	40
Thickness	(ISO 534)	(µm)	57.6
Roughness	(ISO 8791-4)	(µm)	4.2
Brightness D65	(ISO 2470)	(%)	55
L-value D65	(ISO 5631-2)	(D65/10°)	79.2
a-value D65	(ISO 5631-2)	(D65/10°)	-0.4
b-value D65	(ISO 5631-2)	(D65/10°)	1.6
Opacity.	(ISO 2471)	(%)	84

PRODUCT FAMILY:
Directory

FINISH:
Matt

PRINTING METHOD:
Cold set web offset

PRODUCER:
Tasman

Norske Skog Tasman
is certified according
to:

FSC Chain of Custody
ISO 14001:2004
ISO 18001:2007
ISO 9001:2008
Wood Sourcing Policy