

Boyer Vantage Super

End use: Magazines, catalogues, supplements, direct mail, inserts/flyers

100% plantation softwood fibre - All fibre is sourced from well managed plantation forests and other controlled sources - No native timber used - Elemental chlorine free

Basic properties	ISO							
Basis Weight	(ISO 536)	(g/m ²)	57	60	65	70	75	
Thickness	(ISO 534)	(µm)	52	55	60	65	70	
Bulk	(ISO 534)	(cm ³ /g)	0.92	0.92	0.92	0.93	0.93	
Brightness D65	(ISO 2470)	(%)	80	82	85	85	85	
L-value D65	(ISO 5631-2)	(D65/10°)	88	89	90	90	90	
a-value D65	(ISO 5631-2)	(D65/10°)	0.6	0.6	0.6	0.6	0.6	
b-value D65	(ISO 5631-2)	(D65/10°)	-5.5	-5.5	-5.5	-5.5	-5.5	
Opacity.	(ISO 2471)	(%)	92	93	93	94	95	
Gloss Hunter	(ISO 8254-1)	(%)	53	54	55	55	55	

PRODUCT FAMILY:
Vantage LWC

FINISH:
Gloss

PRINTING METHOD:
Heat set web offset

PRODUCER:
Boyer

*Last Updated:
29 September 2016*

Norske Skog Boyer is
certified according to:

Paper Profile Document
AS/ANZ ISO 14001:2015
FSC Forest Management
FSC Chain of Custody
PEFC Chain of Custody