

Boyer Vantage Super

Utilisation finale: Magazines, catalogues, supplements, direct mail, inserts/flyers

100% plantation softwood fibre - All fibre is sourced from well managed plantation forests and other controlled sources - No native timber used - Elemental chlorine free

Caractéristiques de base	ISO						
Grammage	(ISO 536)	(g/m ²)	57	60	65	70	75
Epaisseur	(ISO 534)	(µm)	52	55	60	65	70
Main	(ISO 534)	(cm ³ /g)	0.92	0.92	0.92	0.93	0.93
Blancheur D65	(ISO 2470)	(%)	80	82	85	85	85
Luminance	(ISO 5631-2)	(D65/10°)	88	89	90	90	90
Valeur A	(ISO 5631-2)	(D65/10°)	0.6	0.6	0.6	0.6	0.6
Valeur B	(ISO 5631-2)	(D65/10°)	-5.5	-5.5	-5.5	-5.5	-5.5
Opacité	(ISO 2471)	(%)	92	93	93	94	95
Brillance Hunter	(ISO 8254-1)	(%)	53	54	55	55	55

FAMILLE DE
PRODUITS:
Vantage LWC

MÉTHODE
D'IMPRESSON:
Heat set web offset

*Last Updated:
29 September 2016*

SURFACE:
Gloss

PRODUCTEUR:
Boyer

**Norske Skog Boyer est
certifié selon:**

Paper Profile Document
AS/ANZ ISO 14001:2015
FSC Forest Management
FSC Chain of Custody
PEFC Chain of Custody