

Boyer Vantage LWC

Utilisation finale: Magazines, catalogues, supplements, direct mail, inserts/flyers

- 100% plantation softwood fibre - All fibre is sourced from well managed plantation forests and other controlled sources - No native timber used - Elemental chlorine free

Caractéristiques de base	ISO						
Grammage	(ISO 536)	(g/m ²)	51	54	57	60	65
Epaisseur	(ISO 534)	(µm)	52	54	56	58	61
Main	(ISO 534)	(cm ³ /g)	1.02	1.0	0.98	0.96	0.94
Blancheur D65	(ISO 2470)	(%)	73	73	73	73	73
Luminance	(ISO 5631-2)	(D65/10°)	87	87	87	87	87
Valeur A	(ISO 5631-2)	(D65/10°)	0.2	0.2	0.2	0.2	0.2
Valeur B	(ISO 5631-2)	(D65/10°)	-0.5	-0.5	-0.5	-0.5	-0.5
Opacité	(ISO 2471)	(%)	91	92	93	94	95
Brillance Hunter	(ISO 8254-1)	(%)	43	43	45	45	45

FAMILLE DE
PRODUITS:
Vantage Super

MÉTHODE
D'IMPRESSON:
Heat set web offset

*Last Updated:
29 September 2016*

SURFACE:
Gloss

PRODUCTEUR:
Boyer

**Norske Skog Boyer est
certifié selon:**

Paper Profile Document
AS/ANZ ISO 14001:2015
FSC Forest Management
FSC Chain of Custody
PEFC Chain of Custody