

Saugbrugs NorSC Lite

Utilización final: Magazines, inserts, catalogues, direct mail and door drop.

Propiedad	ISO						
Gramaje	(ISO 536)	(g/m ²)	42	45	47.4	52	56
Espesor	(ISO 534)	(µm)	44	45	46	48	49
Densidad	(ISO 534)	(kg/m ³)	980	1015	1030	1080	1140
Volumen Específico	(ISO 534)	(cm ³ /g)	1.03	1.01	0.97	0.92	0.88
Blancura D 65	(ISO 2470)	(%)	69	69	69	69	69
Blancura CIE	(ISO 11475)	(%)	52	52	52	52	52
Tonalidad L D 65	(ISO 5631-2)	(D65/10°)	88	88	88	88	88
Tonalidad A D 65	(ISO 5631-2)	(D65/10°)	-1.4	-1.4	-1.4	-1.4	-1.4
Tonalidad B D 65	(ISO 5631-2)	(D65/10°)	4.3	4.3	4.3	4.3	4.3
Opacidad	(ISO 2471)	(%)	89	90	91	93	94
Brillo (Hunter)	(ISO 8254-1)	(%)	35	38	41	43	44
Lisura PPS 10	(ISO 8791-4)	(µm)	1.3	1.2	1.2	1.1	1.1

FAMILIA DE PRODUCTOS:

SISTEMA DE IMPRESIÓN:
Heatset & Rotogravure
Characterization data:
Fogra 40

*Last Updated:
May 2019*

ACABADO:
SC

PRODUCTOR:
Saugbrugs

Norske Skog
Saugbrugs tiene la
certificación:

Paper Profile
PEFC
FSC
EU Timber Regulation
ISO 50001: 2011
ISO 9001: 2015
ISO 14001: 2015
EU Ecolabel
click here to see a few of our
customers who are currently
benefiting from Norsc Lite
EU Timber Regulation